



# ŁUKASIEWICZ RESEARCH NETWORK – POZNAŃ INSTITUTE OF TECHNOLOGY

ul. Ewarysta Estkowskiego 6, 61-755 Poznań, Poland  
• tel: +48618504890 • fax: +48618526376 • e-mail: [office@pit.lukasiewicz.gov.pl](mailto:office@pit.lukasiewicz.gov.pl)

## WOOD TECHNOLOGY CENTRE TESTING LABORATORY OF WOOD, WOOD-BASED MATERIALS, PACKAGING, FURNITURE AND CONSTRUCTIONS

ul. Winiarska 1, 60-654 Poznań, Poland  
• tel: +48618492400 • fax: +48618224372 • e-mail: [office.dbd@pit.lukasiewicz.gov.pl](mailto:office.dbd@pit.lukasiewicz.gov.pl)  
• www: <https://pit.lukasiewicz.gov.pl/>

### SOLID BIOFUELS TESTING SECTION



AB 088

Poznań, 10<sup>th</sup> November 2023



# TEST REPORT No. BDB-23-A-4760

<b>Subject of the order</b>	Quality testing of wood pellets – Drewnoland S.C.
<b>Order No</b>	A/DBD/BDB/4760/2023
<b>Name and address of the customer</b>	DIN CERTCO Gesellschaft für Konformitätsbewertung mbH Alboinstrasse 56, 12103 Berlin
<b>Name and address of the producer</b>	Drewnoland S.C.
<b>DINplus ID/ Sample No.</b>	7A450; D-1
<b>Performance date</b>	24.10 – 10.11.2023
<b>Operators</b>	Jacek Pawłowski, M.Sc. Dariusz Radoński, B.Eng. Małgorzata Walkowiak, M.Sc.Eng.

Compiled by

Authorized by

--	--

Małgorzata Walkowiak, M.Sc.Eng.

Wojciech Cichy, PhD.Eng.

*A qualified electronic signature has been affixed to this document, which according to the law is equivalent to written form.*

## 1. IDENTIFICATION (DESCRIPTION OF TEST SAMPLE)

The object of the assessment was the sample of pellets, described by the customer as:

- Sample No: D-1
- Procedure No: 3383003
- Registration No. 7A450

Identification number: A-4760-BDB/2023.

## 2. DELIVERY DATE OF TESTED SUBJECTS

The sample was taken by the customer and delivered to the laboratory on 24<sup>th</sup> October 2023.

## 3. TEST METHODS

- EN ISO 14780:2017-07 Solid biofuels – Sample preparation (Method 16M)
- EN ISO 18134-2:2017-03 Solid biofuels – Determination of moisture content – Oven dry method – Part 2: Total moisture – Simplified method (Method 1M)
- EN ISO 18134-3:2015-11 Solid biofuels – Determination of moisture content – Oven dry method – Part 3: Moisture in general analysis sample (Method 1M)
- EN ISO 18122:2016-01 Solid biofuels – Determination of ash content (Method 2M)
- EN ISO 17828:2016-02 Solid biofuels – Determination of bulk density (Method 4M)
- EN ISO 18125:2017-07 Solid biofuels – Determination of calorific value (Method 6M)
- EN ISO 16948:2015-07 Solid biofuels – Determination of total content of carbon, hydrogen and nitrogen (Method 7M)
- EN ISO 16994:2015-06 Solid biofuels – Determination of total content of sulfur and chlorine (Method 8M)
- EN ISO 18846:2016-11 Solid biofuels – Determination of fines content in quantities of pellets (Method 9M)
- EN ISO 17831-1:2016-02 Solid biofuels – Determination of mechanical durability of pellets and briquettes – Part 1: Pellets (Method 10M)
- EN ISO 17829:2016-02 Solid biofuels – Determination of length and diameter of pellets (Method 11M)
- EN ISO 16968:2015-07 Solid biofuels – Determination of minor elements (Method 13M)
- EN ISO 21404:2020-8 Solid biofuels – Determination of ash melting behaviour (Method 14M)

## 4. EQUIPMENT OF THE TEST STANDS (elementary)

No.	Name	Type	Producer	Lab.No.
1.	Analytical balance	LE26P-0CE	SARTORIUS	M7/2
2.	Analytical balance	CPA225D-0CE	SARTORIUS	M8/57
3.	Laboratory drier	Redline RF115	BINDER	M1/47
4.	Calorimeter	C6000	IKA	M6/83
5.	Elemental analyzer	Flash EA 1112	THERMO ELECTRON CORPORATION	M7/8
6.	Furnace	FCF 7SM/pl	CZYLOK	M2/4
7.	Ionic chromatograph	ICS-1100	THERMO SCIENTIFIC	M8/54
8.	Laboratory balance	WLC 6/F1/R	RADWAG	M9/46
9.	Pellets durability tester	TUMBLER 3000	BIOENERGY ANLAGENPLANUNG	M10/42
10.	Sieve 3.15 mm	-	RETSCH	M9/34
11.	Caliper	SD-10	BAKER	M3/14
12.	Microwave oven	MARS 6	CEM CORPORATION	M13/80
13.	Atomic Absorption Spectrometer	280FS AA	AGILENT TECHNOLOGIES	M13/66
14.	Atomic Absorption Spectrometer	280Ze AA	AGILENT TECHNOLOGIES	M13/67
15.	Mercury analyzer	DMA80	Milestone	M13/117
16.	System for determination of characteristic temperatures of ash melting behaviour	PR-37/1600	Radio Research Institute	M14/88
17.	Sieve 0.075 mm	-	ATEST	M14/91

## 5. TESTS RESULTS

Tests results are presented in record No 1/4760/2023.

## 6. DECLARATION

Test results presented in this Report refer to the tested samples only.

Without written consent of the Laboratory the Report may not be reproduced in any other form than in its entirety.

**Record No. 1/4760/2023**

**Sample name:** Wood pellets  
**Name of Producer:** Drewnoland S.C.  
**DINplus ID /sample No.:** 7A450; D-1

<b>Origin:</b>		1. Woody biomass		
<b>Traded form:</b>		Wood pellets		
<b>Classification of origin according to EN ISO 17225-1:2021</b>		1.2.1 Chemically untreated by-products and residues from the wood processing industry		
<b>Parameter</b>	<b>Unit</b>	<b>Value</b>	<b>Uncertainty [±] <sup>1</sup></b>	<b>Threshold value acc. to DINplus Certification Scheme Edition: November 2021</b>
Diameter	mm	6.0	0.1	6 ± 1 or 8 ± 1
Length	mm	16.7	7.9	3.15 < L ≤ 40
Moisture	w-% <sub>ar</sub>	6.5	0.2	≤ 10
Ash	w-% <sub>d</sub>	0.47	0.02	≤ 0.6
Mechanical durability	w-% <sub>ar</sub>	98.5	0.1	≥ 98.0
Fines (< 3.15 mm)	w-% <sub>ar</sub>	0.11	0.01	≤ 0.5% / ≤ 1.0 % <sup>2</sup>
Gross calorific value	MJ/kg <sub>d</sub>	20.51	0.05	-
Net calorific value	MJ/kg <sub>ar</sub>	17.70	0.09	≥ 16.5
	kWh/kg <sub>ar</sub>	4.92	0.02	≥ 4.6
Bulk density	kg/m <sup>3</sup> <sub>ar</sub>	663	10	600 ≤ BD ≤ 750
Carbon	w-% <sub>d</sub>	50.72	0.53	-
Hydrogen	w-% <sub>d</sub>	6.55	0.24	-
Nitrogen	w-% <sub>d</sub>	0.14	0.02	≤ 0.3
Sulfur	w-% <sub>d</sub>	0.006	0.001	≤ 0.04
Chlorine	w-% <sub>d</sub>	0.014	0.002	≤ 0.02

**Sample name:** Wood pellets  
**Name of Producer:** Drewnoland S.C.  
**DINplus ID /sample No.:** 7A450; D-1

<b>Origin:</b>		1. Woody biomass		
<b>Traded form:</b>		Wood pellets		
<b>Classification of origin according to EN ISO 17225-1:2021</b>		1.2.1 Chemically untreated by-products and residues from the wood processing industry		
<b>Parameter</b>	<b>Unit</b>	<b>Value</b>	<b>Uncertainty [±] <sup>1</sup></b>	<b>Threshold value acc. to DINplus Certification Scheme Edition: November 2021</b>
Ash shrinkage temperature SST <sup>3, 4</sup>	°C	1310	24	Should be stated
Ash deformation temperature DT <sup>3, 4</sup>	°C	1460	51	≥ 1200
Ash hemisphere temperature HT <sup>3, 4</sup>	°C	1480	20	Should be stated
Ash flow temperature FT <sup>3, 4</sup>	°C	1490	13	Should be stated
Arsenic	mg/kg <sub>d</sub>	< 0.1	-	≤ 1
Cadmium	mg/kg <sub>d</sub>	0.35	0.02	≤ 0.5
Chromium	mg/kg <sub>d</sub>	< 0.5	-	≤ 10
Copper	mg/kg <sub>d</sub>	0.98	0.02	≤ 10
Lead	mg/kg <sub>d</sub>	< 0.5	-	≤ 10
Mercury	mg/kg <sub>d</sub>	0.0039	0.0002	≤ 0.1
Nickel	mg/kg <sub>d</sub>	< 0.5	-	≤ 10
Zinc	mg/kg <sub>d</sub>	8.00	0.01	≤ 100

<sub>d</sub> dry, <sub>ar</sub> as received

- the expanded uncertainty was determined for coverage factor  $k = 2$  and 95% confidence level
- "at the factory gate", last loading before delivering to end-user ( $\leq 0.5\%$  small bags up to 20kg;  $\leq 1\%$  large sacks and bulk ware)
- characteristic ash melting temperature determined in an oxidizing atmosphere
- ash received at 815°C

---

End of report